

DALLAS LABORATORIES, INC.

Consultants and Technologists
Chemical and Petroleum Chemists

P.O. BOX 152837, DALLAS, TEXAS 75315
1323 WALL ST, DALLAS, TEXAS 75215
PHONE 214/565-0593
FAX 214/565-1094

MEMBERS
AMERICAN CHEMICAL SOCIETY
ASTM INTERNATIONAL
AMERICAN SOCIETY OF MATERIALS

MEMBERS
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: Flame Safe
2653 Warfield Avenue
Fort Worth, TX 76106

Date: April 24, 2019

Attn: Louis Jacobini

Report No: 52103


REPORT

Lab Sample No.: One (1) Sample
52103 Fire Poly

RESULTS

<u>Test/Method</u>	<u>52103</u>
Non-Volatile, wt % (ASTM D2369)	16.72
Water, wt % (ASTM D4017)	83.08
Density, lb/gal (gr/l) (ASTM D1475)	8.986 (1,076)
VOC, lb/gal (gr/l) (EPA 24)	0.17 (21.0)

DALLAS LABORATORIES, INC.


Kevan W. Jones, Vice President

Analyst: TL
KWJ: js

THE ANALYSIS OF THE ABOVE SAMPLE OR SAMPLES DO NOT IMPLY AN ENDORSEMENT. THIS REPORT OR ANY PART THEREOF MAY NOT BE REPRODUCED OR USED FOR ADVERTISING PURPOSES WITHOUT OUR EXPRESS WRITTEN CONSENT.